

SS Strip-A-Lot



Technical Data Sheet (07/30/14)

BIODEGRADABLE & ENVIRONMENTALLY FRIENDLY COATING STRIPPER

PRODUCT DESCRIPTION

SS Strip-A-Lot is a roll-on paint remover that is biodegradable, very user-friendly, and environmentally safe. It is highly effective in removing even the toughest and most durable industrial coatings such as urethanes and epoxies from surfaces like metal, wood, masonry, brick and especially concrete. SS Strip-A-Lot provides superior stripping capabilities to lift urethanes, alkyd paints, latex paints, lead based paints and varnish, as well as most two component epoxy coatings and fusion bonded epoxies from all types of substrates, including concrete, masonry, steel, aluminium, and metal alloys.

BENEFITS AND FEATURES

- Fully biodegradable, and non-flammable formulation.
- VOC compliant product that contains no carcinogens, and does not deplete the ozone.
- This product's stripping capabilities can save money over high cost mechanical stripping methods.

RECOMMENDED APPLICATIONS

SS Strip-A-Lot is recommended for use on all forms of concrete, paver, and masonry surfaces including broom finish and exposed aggregate driveways, garage and warehouse floors, patios and walkways, and etc.

TECHNICAL INFORMATION

Solids.....	20%	Wet Appearance	Light Beige
Drying Time.....	Refer to Directions	Dry Appearance	White
Re-Coat Time.....	Refer to Directions	VOC Content.....	<100 g/l
Foot Traffic.....	Not Recommended	Blush Resistance	n/a
Wheel Traffic.....	Not Recommended	Solvent Resistance.....	n/a
Application Temp.....	50°F–90°F	Concrete Adhesion.....	n/a

Please note that low air and/or concrete temperatures and/or relative humidity may extend drying times. Follow recommended coverage rates for best results.

SPECIFICATIONS/COMPLIANCES

SS Strip-A-Lot is VOC and OTC compliant in all areas of the United States and many foreign nations.

APPROXIMATE COVERAGE RATES

APPLICATION SURFACE	FIRST COAT	OPTIONAL SECOND COAT	
All recommended surfaces		50–100 ft ²	50–100 ft ²

Coverage rates vary depending upon surface porosity and texture, and application method. Follow directions for best results.

INSTRUCTION FOR USE

Always apply to a test area prior to full application. This will show the time required for approximate project completion, suitability of product for paint and substrate, and most effective method.

SS Strip-A-Lot was designed for roll, spray, or brush application. Airless sprayers are recommended. Use only airless equipment with chemical resistance. A common medium size airless sprayer is capable of spraying this product. Equip the sprayer with a tip size of 0.02 inches or larger. [Examples: a 519 or a 425 tip]. Other equipment should include brushes, rollers, scraper, masking tape, plastic sheet, high GPM (gallon per minute) and PSI pressure washer, electric drill with mixer, empty pails for clean-up, running water, rags. Rollers are recommended for horizontal application only.

Cover and protect areas where stripping is not desired, including adjoining surfaces where over spray may travel. Plastic sheets have shown to be an effective barrier. If using masking tape, apply two layers of tape and remove the top layer immediately after application as the remover may soak through the tape, damaging paint beneath it. Plant life should be covered or washed thoroughly with water before and during application so as to not damage it.

It is not recommended to shake to mix. Using a drill mixer, mix SS Strip-A-Lot until all product is uniform in color and of a creamy consistency (approximately 45 seconds per gallon).

Apply a thick, even layer of stripper onto the coating to be removed. An airless sprayer has shown to be the best means for application. Always start the sprayer pump at the lowest pressure setting, and slowly build up the pressure until the proper fan pattern has been generated. High pressure and narrow tip sizes will break the stripper's emulsion and affect it's integrity. SS Strip-A-Lot must be applied at approximately 2 times the thickness of the coating being removed. When trying to build very thick films, or when trying to apply the stripper on a glossy or greasy vertical surface, it is recommended to apply the stripper via two separate applications. First apply a light coat of approximately 12–15 mils, thick enough to hide the surface color of coating and allow it to dwell for 15 to 30 minutes and then build the rest of the stripper film thickness in a second application. Scrubbing the SS Strip-A-Lot with stiff bristle brush on rough surfaces prior to washing off may increase penetration of stripper. If using a brush to agitate, make sure the underlying surface is completely covered with SS Strip-A-Lot.

Do not allow the stripper to dry out. The stripper is designed to remain wet and effective over extended periods of time (up to 24–48 hours), however, excessive sunshine, windy conditions, or insufficient stripper thickness may cause early drying. Use plastic sheeting to cover stripper to minimize evaporation. If the stripper starts to dry, re-apply a light coat and allow an extended time frame for project completion. Do not rinse with water between applications.

The time required for adequate penetration tends to vary according to the type, the thickness, and the temperature of the coating. Most paint systems require between 2 to 36 hours. SS Strip-A-Lot can be left overnight, but do not allow it to dry out. It is recommended to cover SS Strip-A-Lot with poly sheeting to reduce the drying time and to allow adequate coating penetration.

Removal of lifted paint can be completed by scraper, squeegee, wet/dry vacuum suction system or by high pressure (above 3000 psi) power wash. Scrubbing the SS Strip-A-Lot with stiff bristle brush on rough surfaces prior to washing off may increase penetration of stripper. A scraper works well on smooth surfaces before applying water. If residue still exist on surface after scraping reapply SS Strip-A-Lot allow reasonable dwell time and repeat scraping procedure. Pressure wash into the area to be stripped so residue does not collect on washed areas. Be aware that when using a high GPM and PSI pressure washer, damage can be done to very porous surfaces. Pressure wash from the bottom up on vertical surfaces to prevent rinse water from deactivating stripper in sections below. The stripped surface must be rinsed with water to remove all chemical residue before repainting. Collect lifted paint and dispose of in accordance with local and federal government regulations. Do not collect and/or store removed paint and stripper waste residue in metal containers. Clean up spray equipment by running water through the equipment soon after the spraying has been completed.

CLEAN UP

Use warm soap and water. Dispose of containers in accordance with local and federal regulations.

PRODUCT REMOVAL

Refer to directions.

SHELF LIFE

SS Strip-A-Lot has a shelf life of two years in it's original, sealed, unopened container.

PACKAGING

SS Strip-A-Lot is packaged and stocked in 1 gallon cans and 5 gallon pails (Also available in 55 gallon drums).

PRECAUTIONS AND LIMITATIONS

- SS Strip-A-Lot will not freeze. However, it is recommended to store in an area between 65°F and 85°F recommended.
 - SS Strip-A-Lot will not strip all coatings. Please test prior to the beginning of application.
 - Coverage rates depend upon many conditions including application method, surface porosity, applicator, etc.
 - SS Strip-A-Lot was designed for interior and exterior surfaces.
 - SS Strip-A-Lot should never be thinned or diluted with any kind of chemical or liquid.
 - The statements made within this technical data sheet, SDS, product labels, etc are guidelines only. The end user should always perform tests and product evaluations prior to application to ensure suitability for particular uses.
-

SPECIAL NOTES

Please consult Safety Data Sheet (SDS) and read Warranty information prior to use. This information can be requested by contacting customer service at 866-906-2006.

WARRANTY:

SS Specialties warrants our products to be of good quality, free of defects and will conform to our published specification in force on the date of acceptance of the order. As the exclusive remedy for breach of this warranty, SS Specialties will replace defective materials ninety days after SS Specialties has shipped the product, all our warranty and other duties with respect to the quality of materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates, and no action for breach of any said duties may thereafter be commenced. No warranty is expressed or implied as to the length of life of this product or merchantability or fitness. Liability, if any is limited to the purchase price of the material under no circumstances will SS Specialties be liable for a consequential damage to any in excess of the purchase price of their product

